

**Union bridge. Ready for use.**

**Acrylic adhesive Primer in watery dispersion developed for bonding new mortar to old**

### CONSUMPTION

Primacrete (1 layer ) => 0,10 L/m<sup>2</sup>

This performance varies depending on the porosity of the support.

### APPLICATION

Primacrete is applied by brush or microfiber roller of in one layer.

- Before applying homogenize the product perfectly.
- Apply at temperatures between 5 and 35°C.
- The surface must be free of dust, grease and moisture.
- Let the product dry until it becomes translucent before applying the mortar.
- Never apply more than 1 cm of mortar thickness.



### PROPERTIES

Easy application.



Alkali resistant.



Consolidating.



Great power of adhesion in different substrates.



Low sensitivity to water.

### TECHNICAL DATA

|   |                                    |
|---|------------------------------------|
| <b>Aspect</b>                                 | Milky liquid                       |
| <b>Milky liquid</b>                           | 37% ± 1                            |
| <b>pH</b>                                     | 8.5                                |
| <b>Minimum film forming temperature</b>       | 1 g/mL                             |
| <b>Specific Weight at 20°C</b>                | 1,04 g/cm <sup>3</sup>             |
| <b>RVT Brookfield viscosity at (3/20 rpm)</b> | 1.700 – 2.200 mPa·s                |
| <b>Emulsifying system</b>                     | Not ionic                          |
| <b>Appearance of the film</b>                 | High plasticity                    |
| <b>Touch dry</b>                              | Permanent tack                     |
| <b>Repaintable</b>                            | Up to 15 days from the application |
| <b>Frost stability</b>                        | Very good                          |
| <b>Stability to the outside</b>               | Aliphatic                          |
| <b>Stability to transit</b>                   | None                               |
| <b>Adherence</b>                              | Clean and dry porous surfaces      |
| <b>Finish</b>                                 | Colorless glossy                   |
| <b>Maximum thickness</b>                      | 60 µm                              |



### SPECIAL PRECAUTIONS

The product does not require special handling measures, the following general measures are recommended:

- Avoid contact with eyes and skin.
- Use rubber gloves and glasses.
- In case of contact with eyes: wash with water for 15 minutes.
- In case of ingestion: consult a doctor quickly.

Keep out of the reach of children.

Empty containers must be disposed of in accordance with current legal regulations.

### STORAGE CONDITIONS

The products of Luxury Concrete should be stored in their closed original packaging, sheltered from the weather at temperatures between 5°C and 30°C in a dry and well ventilated place, away from direct heat and sunlight. Shelf life is 1 year from the date of manufacturing, if stored correctly.

The product should not be used for purposes other than those specified without first having instructions in writing. It is always the user's responsibility to take suitable measures in order to comply with the requirements established in local legislation. Product safety sheets are available for professionals. This technical data sheet will be valid until a new edition appears.



### PACKAGING

Available in 5 and 25 litre plastic container

